

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 88305705.1

(51) Int. Cl.⁴: G02B 6/44

(22) Date of filing: 22.06.88

(30) Priority: 23.06.87 GB 8714640

(33) Date of publication of application:
28.12.88 Bulletin 88/52

(84) Designated Contracting States:
AT BE CH DE ES FR GB GR IT LI LU NL SE

(71) Applicant: BICC Public Limited Company
Devonshire House Mayfair Place
London W1X 5FH(GB)

Applicant: CORNING LIMITED
Wear Glass Works
Sunderland SR4 6EJ(GB)


(72) Inventor: Rodney John Davey
9 Ralton Close, Rainhill
Prescott, Merseyside L35 0QD(GB)
Inventor: Sadler Alan Arthur
2 Eversley Close, Frodsham
Warrington, Cheshire WA6 6AZ(GB)

(74) Representative: Boon, Graham Anthony et al
Elkington and Fife High Holborn House 52/54
High Holborn
London, WC1V 6SH(GB)

(54) Optical fibre cables.

(57) An optical fibre cable comprises an inner sheath (3) containing at least one optical fibre member (1,2), and an outer sheath (5) containing the inner sheath (3). The inner sheath (3) is of a material which is soft and has a low modulus of elasticity. The outer sheath (5) of a material having bulk properties, such as density and stiffness, and surface properties, such as surface texture and friction such that the cable can be propelled along a duct by a flow of air travelling along the duct.

An intermediate sheath (4) may be provided between the inner and outer sheaths (3, 5).



EP 0 296 836 A1

BEST AVAILABLE COPY

OPTICAL FIBRE CABLES

This invention relates to optical fibre cables.

EP-A-108590⁺ describes a method of installing an optical fibre cable in which the cable is propelled along a previously installed duct by fluid drag of a gaseous medium, preferably air, blown along the duct in the desired direction of cable advance. EP-A-108590 describes a number of designs of cables for installation using the method of the invention (hereinafter referred to as the "blown fibre method"), but preferred cable designs for use in the blown fibre method are described in EP-A-157610. The designs of EP-A-157610 use an inner sheath containing one or more optical fibre, and an outer sheath containing the inner sheath. The outer sheath is of a material having a low density, for example a foam, and it is this which reduces the overall density of the cable to a value sufficiently low for it to be blown satisfactorily.

An object of the present invention is to provide an improved design of optical fibre cable which can be installed using the blown fibre method.

According to the present invention there is provided an optical fibre cable comprising an inner sheath containing at least one optical fibre, and an outer sheath containing the inner sheath, the inner sheath being of a material which is soft and has a low modulus of elasticity, and the outer sheath having bulk and surface properties such that the cable can be propelled along a duct by air blown along the duct.

An intermediate layer may be provided between the inner and outer sheaths, with the intermediate layer being chosen to provide, for example, additional mechanical strength and/or environmental protection for the fibres.

An embodiment of the present invention is shown in cross-section in the accompanying drawing, which is not to scale.

The drawing shows a cable comprising a plurality of optical fibres 1 made, for example, of silica. In the illustrated embodiment four such fibres are shown, but there could be more or less as described. Each fibre is surrounded by a protective coating 2, for example of a UV-cured acrylate resin. Typically each fibre 1 has a diameter of 125 microns and the thickness of the coating 2 is such as to bring the overall diameter of the fibre 1 plus coating 2 up to about 250 microns. A fibre 1 plus its coating 2 is referred to as a fibre member in the following description.

The fibre members are surrounded by an inner sheath 3 of a material which is soft and has a low modulus of elasticity. The sheath 3 may, for example, be formed of acrylate or thermoplastic rubber. An intermediate layer 4 surrounds the sheath 3. The layer 4 is preferably of a material which is hard and has a high modulus of elasticity, so as to confer mechanical protection on the soft sheath 3 and the fibre members which the sheath contains. If desired, the intermediate layer 4 could be chosen to be of a material having a low permeability of moisture vapour and good resistance to chemical attack, so as to provide environmental protection for the sheath 3 and the fibre members.

The intermediate layer 4 is surrounded by an outer sheath 5 of a material, for example, a foam, having a low density, e.g. 0.6. Examples of materials which could be used for this purpose are foamed polyethylene and foamed acrylate, the latter having the advantage of a lower coefficient of thermal expansion. The bulk and surface properties of the sheath 5 are such that it can be blown satisfactorily in the blown fibre method. By "bulk properties" we refer primarily to density and stiffness, and by "surface properties" we refer primarily to surface texture and friction. Typically the sheath 5 may have a low density. Typically, the outer diameter of the sheath 3 is 0.8 mm, that of the layer 4 is 1.0mm and that of the sheath 5 is 1.7mm. These dimensions are appropriate for a four-fibre cable, but would of course vary for cables having more or less than four fibres.

Reverting to the inner sheath 3, it will be seen that this contacts substantially the whole exterior surface of the fibre members, except for the interior space 6 defined between the fibre members. If, as would be convenient, the sheath 3 were applied to the fibre members by an extrusion process it would be difficult to fill the space 6 with the sheath material. It is conceivable, however, that some other method might be used for application of the sheath 3, in which case the space 6 might also be filled with sheath material, for example to resist longitudinal penetration of liquid and gaseous media and to support substantially all of the surface area of the fibre members, thus improving stability.

Since the inner sheath 3 is formed of a material which has a low modulus of elasticity it serves to distribute any stresses arising within the cable in a reasonably uniform fashion, particularly where the space 6 is also filled. This contrasts with the preferred design disclosed in EP-A-157610 where there is an inner sheath formed of a material of high modulus of elasticity which holds the fibre members tightly together along lines of contact. Although the material of the sheath 3 has a low modulus of elasticity, allowing elastic deformation of the structure, it is nevertheless adequate to retain its structural integrity through manufactur-

ing and installation operations. The uniform distribution of stresses and large area of contact of the soft inner layer reduces stress at the interface with the fibres, thus reducing the risk of microbending, either during processing or in service. This is of particular value where the cable is liable to be subject to wide variations in temperatures, since such temperature variations give rise to forces which are liable to cause increased attenuation in the optical fibres. Desirably, the material of the sheath 3 has a coefficient of thermal expansion as close as possible to that of silica, so as to reduce stress on the fibre from changes in temperature. However, the low modulus of elasticity of the material renders it less important than it would otherwise be to select a material for the sheath 3 having a particular coefficient of thermal expansion.

The material and application process for sheath 3 are preferably such as to avoid strong adhesion to the fibres. This, combined with its softness allows it to be removed easily from around the fibre members when preparing the cable for connection to external connectors or when the individual fibre members have to be routed separately from one another.

Various modifications are possible to the embodiment shown in the drawing. As already mentioned, the intermediate layer 4 may be omitted, and this layer may not be required if the sheaths 3 and 5 by themselves provide adequate protection for the fibre members. In another modification, an all-plastic fibre may be used in place of an acrylate-coated silica fibre.

The following table sets out, by way of example, some properties for the materials of which the cable may be made.

TABLE

	Hardness (Shore scale)	Modulus of elasticity (Young's modulus)	Thermal coefficient of expansion
Fibre 1	-	$7.3 \times 10^4 \text{ N/mm}^2$	$4 \times 10^{-7}/^\circ \text{C}$
Acrylate 2	-	-	$6 \times 10^{-5}/^\circ \text{C}$
Sheath 3	40A - 60A	$< 100 \text{ N/mm}^2$	$< 3 \times 10^{-5}$
Layer 4	$> 75 \text{ D}$	$> 900 \text{ N/mm}^2$	$< 1.1 \times 10^{-4}/^\circ \text{C}$
Sheath 5	-	$c. 100 \text{ N/mm}^2$	$2 \times 10^{-4}/^\circ \text{C}$
Sheath 5	-	$c. 100 \text{ N/mm}^2$	$5 \times 10^{-5}/^\circ \text{C}$

* Sheath of foamed polyethylene

~ Sheath of foamed acrylate

In the foregoing reference has been made to a cable as being blowable. It is believed that it will be understood by those skilled in the art whether a given cable is or is not to be regarded as blowable. However, one test which can be employed is as follows. A 50m length of duct having a circular internal cross-section 4.0mm in diameter is wound in a single layer around the outside of a cylindrical drum 0.75m in diameter. A 50m length of cable to be tested is then inserted completely into the duct by any suitable method, which may, but need not, be a blowing method.

An air flow of 20 standard litres/minute is then established down the duct. The time taken for the cable to emerge completely from the downstream end of the duct is recorded. If this fails to occur, or does so in a time greater than a pre-set time, the cable is regarded as not being blowable. The pre-set time may be as long as 1 hour, but is preferably not more than 10 minutes, more preferably not more than 5 minutes, and still more preferably not more than 1 minute. A cable which is highly blowable may emerge in as little as 20 seconds. For the purposes of the test the static coefficient of friction between the cable and the duct is taken to be 0.15. If in fact the coefficient of friction is different an appropriate modification is made to the times quoted above.


The above test is designed for a cable as shown in Figure 1. Appropriate modifications would be made for cables of other designs.

Claims

1. An optical fibre cable comprising an inner sheath containing at least one optical fibre member, and an outer sheath containing the inner sheath, the inner sheath being of a material which is soft and has a low modulus of elasticity, and the outer sheath being of a material having bulk and surface properties such that the cable can be propelled along a duct by a flow of air travelling along the duct.
2. A cable according to claim 1, comprising an intermediate sheath between the inner and outer sheaths.
3. A cable according to claim 2, wherein the intermediate sheath is of a material which is hard and has a high modulus of elasticity.
4. A cable according to claim 2 or 3, wherein the intermediate sheath is of a material which has a low permeability to moisture vapour and good resistance to chemical attack.
5. A cable according to any preceding claim, wherein the inner sheath contacts the or each fibre member over at least a substantial portion of its exterior surface.
6. A cable according to claim 5, wherein there is plurality of optical fibre members so arranged as to create at least one interstice between them, and the material of the inner sheath at least substantially fills the or each interstice.
7. A cable according to any preceding claim, wherein the or each optical fibre member comprises a silica fibre surrounded by a protective coating.
8. A cable according to any preceding claim, having values for hardness, modulus of elasticity and thermal coefficient of expansion selected in accordance with the preceding Table.
9. A cable according to any preceding claim, wherein the outer sheath is of a material having a low density.

20 07 88

Neu eingereicht / Newly filed
Nouvellement déposé





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 88 30 5705

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 4)
Y,D	EP-A-0 157 610 (BRITISH TELECOMMUNICATIONS plc) * Pages 1-3; claims; figures *	1	G 02 B 6/44
A	---	5,7,8,9	
Y	DE-A-2 641 166 (LES CABLES DE LYON S.A.) * Claims *	1	
A	---	3	
A	GB-A-2 096 353 (SOCIETA CAVI PIRELLI SpA) * Abstract *	2	
A	---		
A	DE-A-3 219 455 (SIEMENS AG) * Claims *	2	
A	---		
A	GB-A-2 122 367 (STANDARD TELEPHONES & CABLES PUBLIC LTD. CO.) * Abstract *	1	
A,D	---		TECHNICAL FIELDS SEARCHED (Int. Cl. 4)
	EP-A-0 108 590 (BRITISH TELECOMMUNICATIONS) * Abstract *	1	G 02 B
A	---		
A	GB-A-2 156 837 (BRITISH TELECOMMUNICATIONS plc) * Abstract *	1	

The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 06-10-1988	Examiner PFAHLER R.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document	

In the foregoing reference has been made to a cable as being blowable. The following test is used to determine whether a cable is "blowable" within the meaning of the present invention. A 50m length of duct having a circular internal cross-section 4.0mm in diameter is wound in a single layer around the outside of a cylindrical drum 0.75m in diameter. A 50m length of cable to be tested is then inserted completely into the duct by any suitable method, which may, but need not, be a blowing method. An air flow of 20 standard litres/minute is then established down the duct. The time taken for the cable to emerge completely from the downstream end of the duct is recorded. If this fails to occur, or does so in a time greater than a pre-set time of 1 hour, the cable is regarded as not being blowable. The cable preferably emerges completely in not more than 10 minutes, more preferably not more than 5 minutes, and still more preferably not more than 1 minute. A cable which is highly blowable may emerge in as little as 20 seconds. For the purposes of the test the static coefficient of friction between the cable and the duct is taken to be 0.15. If in fact the coefficient of friction is different an appropriate modification is made to the times quoted above.

The above test is designed for a cable as shown in Figure 1. Appropriate modifications would be made for cables of other designs.

Claims

1. An optical fibre cable comprising an inner sheath (3) containing at least one coated optical fibre member (1,2), and an outer sheath containing the inner sheath, the outer sheath (5) being of a material having bulk and surface properties such that the cable is blowable along a previously installed duct by fluid drag of a gaseous medium as determined by a test in which:
 - (a) a 50 m length of duct having a circular internal cross-section 4.0 mm in diameter is wound in a single layer around the outside of a cylindrical drum 0.75 m in diameter, the static coefficient of friction between the cable and the duct being 0.15;
 - (b) a 50 m length of the cable is inserted completely into the duct by any suitable method;
 - (c) an air flow of 20 standard litres/minute is established down the duct; and
 - (d) the time taken for the cable to emerge completely from the downstream end of the duct is recorded, the cable being regarded as blowable if the said time is not greater than 1 hour, the internal cross-section of the duct and the air flow being appropriately modified from the values of 4.0mm and 20 standard litres/minute respectively if the diameter of the cable differs from 1.7mm.,
 characterized in that the inner sheath (3) is of a material which has a Shore hardness of not more than 60A and has a modulus of elasticity of less than 100MPa.
2. A cable according to claim 1, wherein the outer sheath (5) is in direct contact with the inner sheath (3).
3. A cable according to claim 1, comprising an intermediate sheath (4) between the inner and outer sheaths.
4. A cable according to claim 3, wherein the intermediate sheath (4) is of a material which is hard and has a high modulus of elasticity.
5. A cable according to claim 3 or 4, wherein the intermediate sheath (4) is of a material which has a low permeability to moisture vapour and good resistance to chemical attack.
6. A cable according to any preceding claim, wherein the inner sheath (4) contacts the or each fibre member (1,2) over at least a substantial portion of its exterior surface.
7. A cable according to claim 6, wherein there is plurality of optical fibre members (1,2) so arranged as to create at least one interstice between them, and the material of the inner sheath (3) at least substantially fills the or each interstice.
8. A cable according to any preceding claim, wherein the or each optical fibre member (1,2) comprises a silica fibre (1) surrounded by a protective coating (2).
9. A cable according to any preceding claim, having values for hardness, modulus of elasticity and thermal coefficient of expansion selected from the following Table:

	Hardness (Shore scale)	Modulus of elasticity (Young's modulus)	Thermal coefficient of expansion
5			
Fibre (1)	-	$7.3 \times 10^4 \text{ N/mm}^2$	$4 \times 10^{-7}/^\circ\text{C}$
10			
Protective coating (2)	-	-	$6 \times 10^{-5}/^\circ\text{C}$
Inner sheath (3)	40A - 60A	$< 100 \text{ N/mm}^2$	$< 3 \times 10^{-4}/^\circ\text{C}$
15			
Inter- mediate sheath (4)	$> 75\text{D}$	$> 900 \text{ N/mm}^2$	$< 1.1 \times 10^{-4}/^\circ\text{C}$
20			
Outer sheath (5)	-	$\text{c. } 100 \text{ N/mm}^2$	-

10. A cable according to any preceding claim, wherein the outer sheath (5) is of a material having a low density.

25

Patentansprüche

1. Optisches Faserkabel, das umfaßt eine innere Hülle (3), die mindestens ein beschichtetes optisches Faserelement (1, 2) enthält, und eine äußere Hülle (5), welche die innere Hülle enthält, wobei die äußere Hülle (5) aus einem Material mit solchen Bulk- und Oberflächeneigenschaften ist, daß das Kabel entlang einer vorher installierten Rohrleitung durch einen Fluidstrom aus einem gasförmigen Medium blasbar ist, bestimmt nach einem Test, bei dem
 - a) ein 50 m-Stück einer Rohrleitung mit einem kreisförmigen inneren Querschnitt von 4,0 mm im Durchmesser in Form einer einzelnen Schicht um die Außenseite einer zylindrischen Trommel mit einem Durchmesser von 0,75 m gewickelt wird, wobei der statische Reibungskoeffizient zwischen dem Kabel und der Rohrleitung 0,15 beträgt;
 - b) ein 50 m-Stück des Kabels nach irgendeinem geeigneten Verfahren vollständig in die Rohrleitung eingeführt wird;
 - c) ein Luftstrom aus 20 Standard-Litern/min in der Rohrleitung nach unten erzeugt wird; und
 - d) die Zeit, die das Kabel braucht, um aus dem stromabwärts gelegenen Ende der Rohrleitung vollständig auszutreten, aufgezeichnet wird, wobei das Kabel als blasbar angesehen wird, wenn diese Zeit nicht mehr als 1 h beträgt, wobei der innere Querschnitt der Rohrleitung und der Luftstrom in geeigneter Weise modifiziert werden gegenüber den Werten von 4,0 mm bzw. 20 Standard-Litern/min, wenn der Durchmesser des Kabels von 1,7 mm verschieden ist, dadurch gekennzeichnet, daß die innere Hülle (3) aus einem Material besteht, das eine Shore-Härte von nicht mehr als 60A und einen Elastizitätsmodul von weniger als 100 MPa hat.
2. Kabel nach Anspruch 1, bei dem die äußere Hülle (5) in direktem Kontakt mit der inneren Hülle (3) steht.
3. Kabel nach Anspruch 1, das zwischen der inneren Hülle und der äußeren Hülle eine dazwischen liegende Hülle (4) aufweist.
4. Kabel nach Anspruch 3, bei dem die mittlere Hülle (4) aus einem Material besteht, das hart ist und einen hohen Elastizitätsmodul hat.
5. Kabel nach Anspruch 3 oder 4, bei dem die mittlere Hülle (4) aus einem Material besteht, das eine geringe Durchlässigkeit für Feuchtigkeitsdampf und eine gute Beständigkeit gegen chemischen Angriff hat.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.